

# Ancienne Belgique 7 Camel



## COLOUR

A blend of camel brown and dark brown shades

## Product description

The bricks are formed individually in the unsanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an unsanded surface structure. The shape is slightly irregular. Finally the bricks are processed until they have acquired a weathered shape, due to which the paver surface leaves a rustic, aged impression.

## TECHNICAL CHARACTERISTICS

The pavers are delivered with the following characteristics, in accordance with the CE and UKCA mark:

### CE label according to EN 1344 : 2013 / AC : 2015

Manufacturing dimensions (L x W x H) : \*188x45x63 mm

Quantity / m<sup>2</sup> with a traditional joint : ca. 111

## PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

Aspect	Class	Mean	Individual
Water absorption NBN EN771	Class W2	max 5%	max 6%
Transverse breaking load NBN EN1344	Class T4	min 80 N/mm	min 64 N/mm
Abrasion resistance NBN EN1344	Class A2+	Max 600 mm <sup>3</sup>	max 800 mm <sup>3</sup>
Frost resistance NBN EN1344	Class FP100	freeze/thaw resistant	freeze/thaw resistant
Size tolerance NBN EN1344	Class R1	$\pm 0,4 \sqrt{d}$	0,6 $\sqrt{d}$ (range)
Wet skid resistance NBN EN1344	Class U3	>55	
Acid resistance NBN EN1344	Klasse C	< 7%	



**VANDE MOORTEL**  
CLAY PAVERS • FACING BRICKS • SLIPS

ORIGIN : VANDE MOORTEL NV | Scheldekant 5 | BE-9700 OUDENAARDE |  
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - [info@vandemoortel.co.uk](mailto:info@vandemoortel.co.uk)

# Ancienne Belgique 7 Camel

## Productshot

