SeptimA Onyx

CLAY PAVERS



COLOUR

Black brown

Product description

The bricks are formed individually in the unsanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an unsanded surface structure. The shape is slightly irregular. Finally the bricks are processed until they have acquired a weathered shape, due to which the paver surface leaves a rustic, aged impression.

TECHNICAL CHARACTERISTICS

The paving is laid in fired clay bricks of Belgian origin, quality class A, carrying the CE and UKCA mark.

CE label according to EN 1344: 2013 / AC: 2015

Manufacturing dimensions (L x W x H): *212x50x70 mm

Quantity / m² with a traditional joint: ca. 91

PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

Aspect	Class	Mean	Individual
Water absorption NBN EN771	W3	Max 3%	Max 4%
Transverse breaking load	T4	Min 80 N/mm	Min 64 N/mm
Abrasion resistance	A3	Max 450 mm³	Max 500 mm ³
Frost resistance	FP100	freeze/thaw resistant	freeze/thaw resistant
Wet skid resistance	U3	>55	
Acid resistance	С	< 7%	
Size tolerance*	NPD	NPD	NPD



SeptimA Onyx

CLAY PAVERS



