# **Old Volkeghem**

FACING BRICKS CATEGORY I, U



### **TEXTURE, TYPE & COLOUR**

The decorative brickwork (inside and/or outside face) is made with a solid sanded moulded brick with a rustic view and white and grey cement residuesThe colour is terracotta with white and grey cement residues.

### **RAW MATERIAL & PRODUCTION & VIEWS**

This entirely natural product is made of alluvial clay from the Quaternary from the Scheldt valley. The brick is formed in a mould by putting in a lump of clay and is fired at at least 1150 °C and tumbled. The facing brick is a solid moulded brick and has a homogeneous structure. The pallets may contain approx. 10 to 15% half and three-quarter bricks.

### **TECHNICAL CHARACTERISTICS**

The bricks are delivered with the following characteristics, in accordance with the CE and UKCA mark:

# CE mark according to EN 771-1: 2011 + A1: 2015 and UKCA mark according to BS EN 771-1: 2011 + A1: 2015

Manufacturing dimensions (L x W x H)	: *224x74x54 mm	ECO-7-size
Quantity / m² with a traditional joint	: ca. 65 (12 mm)	***************************************
Gross mass density	: 1900 kg/m³ (+/- 20 %)	***************************************
Avg. standardised compressive strength (cat I)	: > 20 N/mm²	***************************************
Water absorption (24 hours)	: < 16%	***************************************
Initial water absorption (1 minute)	: < 4 kg/(m² . min ) IW3	***************************************
Water vapour permeability	: μ = 5/10	***************************************
Thermal properties (λ10, dry, 90/90)	: 0.60 W/mK (table 1 EN1745)	***************************************
Durability (frost / thaw / resistance)	: F2	***************************************
Active soluble salts	: class S2	***************************************
Fire reaction	: class A1	***************************************

Bond strength (according to EN998-2: 2003 Annex C) : NPD (no performance determined)

## TREATMENT COUNCIL

During processing the bricks should be mixed from 5 different packs. The bricks are stacked tower by tower. The right mortar composition must be determined in consultation with the mortar supplier. Fresh brickwork should always be protected.

\*Dimensions may vary depending on the production. For the most recent version see www.vandemoortel.co.uk. This document is not binding and annuls all previous publications. The manufacturer reserves the right to change the product range and characteristics. The user must always check that he has the most recent descriptive text.



01-08-2025

# **Old Volkeghem**

# **Productshot**



